

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE



Certificato n°  
50 100 4582



Diploma  
IWR/IT n°  
30438



Socio



Membro



Socio

Unione Industriali  
Modena



Iscritto

Modena, 25/02/16

To LAPITEC S.p.A.  
Via Bassanese, 6 31050 Veduggio (TV)  
Italy

Attn. **Sig. TONELLATO****MATERIAL and/or SAMPLE to be tested** : SINTERED STONES;**Denomination of the Sample** : LAPITEC SINTERED STONE DUNE;

Client Reference: Your delivery VS CONSEGNA

date: 13/01/2016

Here attached, you will receive the Test Report of Serial No. **20161041**/n, which shows the results of tests required.

**MODENA CENTRO PROVE**

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

**TEST REPORT: 20161041/1**

Modena, 25/02/16

**CUSTOMER**

LAPITEC S.p.A.  
Via Bassanese, 6 31050 Vedelago (TV) Italy

**MATERIAL and/o SAMPLE to be tested**

SINTERED STONES;

**Denomination**

LAPITEC SINTERED STONE DUNE;

**Date of sample reception**

13/01/2016;

**Kind of test executed**

Determination of Slip Resistance

**Referring standards**

UNI EN 14231:2004

**Shifting from standards**

None

**Equipment**

Pendulum cod. MCP C45

**Calibration**

Rapporto n° 1203244FRI del 30/03/2012

**Subcontracted phases**

None

**Sampling made by**

Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.  
The times of retain of the samples was indicated in the offer related to the test report.*

**Examiner**  
  
P.I. Fili Thomas

MODENA CENTRO PROVE  
  
Ceramic Dept. Responsible  
P.I. De Pasquale Roberto

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

**DETERMINATION OF SLIP RESISTANCE**

Beginning date : 02/19/2016

Analysis ending date : 02/19/2016

**SAMPLE** : sintered stones marked " LAPITEC SINTERED STONE DUNE "  
**SPECIMEN** :

The test was performed measuring friction resistance between standard rubber surface and the upper side of test specimens.

**RESULTS**

Wet slipping element and samples used.

Sample N°	Single values(USRV) two directions average
1	36
2	36
3	37
4	37
5	37
6	37
Average	37

**REQUIREMENTS**

( Norm EN 1341 )

Safety surface with USRV values &gt; 35

**Examiner**  
  
P.I. Fili Thomas

MODENA CENTRO PROVE  
  
Ceramic Dept. Responsible  
P.I. De Pasquale Roberto

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe