

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE



Certificato n°
50 100 4582



Diploma
IWR/IT n°
30438



Socio



Membro



Socio

Unione Industriali
Modena



Iscritto

ASSOCIATO



ACIMAC

ASSOCIATED

Modena, 18/03/15

To **LAPITEC SPA**
VIA BASSANESE, 6
31050 VIDELAGO (TV) ITALY

Attn. **C. TONELLATO**

MATERIAL and/or SAMPLE to be tested : SINTERED STONE;

Denomination of the Sample : LAPITEC SATIN COLLECTION;

Client Reference: Your delivery VS CONSEGNA

date: 03/03/2015

Here attached, you will receive the Test Report of Serial No. **20151527**/n, which shows the results of tests required.

MODENA CENTRO PROVE

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

TEST REPORT: 20151527/1

Modena, 18/03/15

CUSTOMER	LAPITEC SPA - - VIA BASSANESE, 6 - 31030 - 31050 VIDELAGO (TV)
MATERIAL and/o SAMPLE to be tested	ITALY
Denomination	SINTERED STONE;
Date of sample reception	LAPITEC SATIN COLLECTION;
Kind of test executed	03/03/2015;
Referring standards	Determination of Slip Resistance
Shifting from standards	UNI EN 14231:2004
Equipment	None
Calibration	Pendulum cod. MCP C45
Subcontracted phases	Rapporto n° 1203244FRI del 30/03/2012
Sampling made by	None
	Customer

The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.

Examiner

P.I. Fili Thomas

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.
Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

DETERMINATION OF SLIP RESISTANCE

Beginning date : 03/12/2015

Analysis ending date : 03/12/2015

SAMPLE : sintered stone sample marked " LAPITEC SATIN COLLECTION "
SPECIMEN :

The test was performed measuring friction resistance between standard rubber surface and the upper side of test specimens.

RESULTS

dry slipping element and samples used.

Sample N°	Single values(USRV) two directions average
1	38
2	39
3	37
4	35
5	37
6	40
Average	38

wet slipping element and samples used.

Sample N°	Single values(USRV) two directions average
1	24
2	22
3	22
4	22
5	22
6	22
Average	22

REQUIREMENTS

(Norm EN 1341)

Safety surface with USRV values > 35

Examiner
Thomas
P.I. Fili Thomas

MODENA CENTRO PROVE
Roberto De Pasquale
Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE
Giuseppe
Director
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

Examiner
Thomas
P.I. Fili Thomas

MODENA CENTRO PROVE
Roberto De Pasquale
Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE
Giuseppe Sant'Unione
Director
Sant'Unione dr. Giuseppe