

SEDE

Via Martelli, 26 - 40138 **Bologna**
Tel. (051) 534015 - Fax. (051) 530085

CERTI.CER.

LABORATORIO DI ZONA

Via Valle d'Aosta, 1 - 41049 **Sassuolo**
Tel. e Fax. (0536) 802154

Part. IVA 0094778-0375

Bologna, 18/10/13

Spett.le
LAPITEC S.p.A.
Via Bassanese, 6
31050 VEDELAGO (TV)

TEST LABORATORY

TEST REPORT No. 6449/13

(translation of Test Report No. 6387/13 of 16/10/13)

Requested by:	LAPITEC S.p.A. Via Bassanese, 6 31050 VEDELAGO (TV)
On (date):	08/10/13
For the sample marked:	"LAPITEC COLLECTION VESUVIO".

The results reported relate only to the samples tested.

No responsibility is taken for the accuracy of the sampling unless it is done under our supervision.

The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages this cover included.



Consorzio universitario per la gestione del
«Centro di ricerca e sperimentazione per
l'industria ceramica».
D.P.R. 10-4-1978 n. 806
(G.U. 20-12-1978 n. 353)

Laboratorio autorizzato ad effettuare il
servizio di rilevamento dell'inquinamento
atmosferico.
Decreto MINISTERO SANITÀ 10-8-1974
(G.U. 14-9-1974 n. 240)

Laboratorio iscritto nell'albo dei «Laboratori Esterni
Pubblici e Privati Altamente Qualificati».
Decreto MINISTERO RICERCA SCIENTIFICA 6-6-1983
(G.U. 6-7-1983 n. 183)

Membro ASTM
American Society for
Testing and Materials.

Description of the sample:

Slab 50 x 120 cm marked "LAPITEC COLLECTION VESUVIO".

Manufacturer: -----.

Sampling details:

- Where: -----
 - Date: -----
 - By whom: CUSTOMER
 - How (methods): -----

DATE OF RECEIVAL IN LABORATORY: 11/10/13

TESTS PERFORMED:

		Date of starting	Date of ending
<input checked="" type="checkbox"/>	DIN 51130 Determination of the anti - slip properties – (06/2004) Workrooms and fields of activities with raised slip danger, walking method – ramp test	14/10/13	14/10/13


**DIN 51130 (06/2004)- Determination of the anti - slip properties –
Workrooms and fields of activities with raised slip danger, walking
method – ramp test**

Surface characteristics

- ☐ Smooth
☒ Profiled
☐ Structured
☐ Rough

OPERATIVE CONDITIONS

Fixing scheme

**RESULTS**

Average total acceptance angle:

Movement area (cm³/dm²):

12.3°

CLASSIFICATION (BGR 181- 10/2003)

Group of anti - slip properties:

Movement area evaluation group:

R10

Prof. Eng. Giorgio Timellini
Director